# **TECHNICAL DATA SHEET** DX46 2K HS STANDARD CLEAR





### DESCRIPTION

DX46 2K HS Standard Clear is part of the Duxone repair system and is suitable for use in a clear-over-base system. This high solids universal clear has very good flow in application and delivers a good, long-lasting high-gloss finish. It can be air dried, dried on low bake or using IR, which can help improve a bodyshop's efficiency.

#### **FEATURES**

- · Very good flow.
- · Superb polishability.
- Excellent mar, chemical and weather resistance.
- Suitable for spot, panel and overall repairs.

#### **PRODUCT LIST**

- DX46 2K HS Standard Clear
- DX18 Activator Slow
- DX20 Activator Standard
- DX24 Activator Extra Fast





### **Product preparation - application STANDARD**



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Duxone Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application Existing finishes: Surfaces must be sanded and degreased before application

	Large surface		Spot & panel repair		Standard	
	Volume	Weight	Volume	Weight	Volume	Weight
DX46	2	100	2	100	2	100
DX18	1	50	-	-	-	-
DX20	-	-	-	-	1	49
DX24	-	-	1	50	-	-



Pot life at 20°C: 3 hr 30 min

	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure

see manufacturer's instructions

2 coats

60 - 65 °C



	DX24	DX20	DX18
20 °C	4 hr	5 hr	6 hr

30 min



Guideline for short wave IR equipment Half power: 5 min Full power: 8 - 12 min

20 min

VOC compliant

This product mix is not VOC compliant.

intermediate and final flash-off: 5 min - 10 min

40 min

## **TECHNICAL DATA SHEET DX46 2K HS STANDARD CLEAR**




### Products

DX46 2K HS Standard Clear

- DX18 Activator Slow
- DX20 Activator Standard
- DX24 Activator Extra Fast

### **Product mix**



Mixing ratios with special agents are available in the productmix table on Colour Room and in the specific TDS.



ISO 4: 28 - 37 s at 20°C DIN 4: 14 - 16 s at 20°C

1		-	Τ.	
L	J	F	L	

50 - 60 µm

sanding

Theoretical coverage	360 - 370 m <sup>2</sup> /l at 1 micron dry film thickness Due to different activator characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary. Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.
	DX46 2K HS Standard Clear can be overcoated with itself within 24 hours, without intermediate



Clean after use with a suitable solventbased guncleaner.

### Remarks

- Material has to be at room temperature (18-25°C) before use.
- · Allow additional time for preheating up to panel temperature.
- · Surplus ready for use material should not be returned to original can.
- · Close can of Activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- If necessary for minor viscosity adjustments, use Duxone basecoat Thinner (maximum 5%).
- · Not to be used with Duxone Waterborne Basecoat.

## **TECHNICAL DATA SHEET** DX46 2K HS STANDARD CLEAR



Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Duxone product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Duxone product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.