# **DX49**

### 2K HS EFFECTIVE CLEAR





#### **DESCRIPTION**

DX49 2K HS Effective Clear is part of the Duxone repair system and is suitable for use in a clear-over-base system. This high solids, robust and easy-to-use clear is versatile and delivers excellent finished appearance.

#### **FEATURES**

- Simple to apply.
- · No thinner required.
- Excellent sagging resistance.
- · Fast drying.
- Good mar resistance.
- · Milky clear with no negative impact on colour.
- Suitable for spot, panel and overall repairs.

#### PRODUCT LIST

- DX49 2K HS Effective Clear
- DX18 Activator Slow
- DX20 Activator Standard
- · DX24 Activator Extra Fast



# DX49 2K HS EFFECTIVE CLEAR



### Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.





Duxone Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application Existing finishes: Surfaces must be sanded and degreased before application



	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
DX49	2	100	2	100	2	100
DX18	-	-	-	-	1	51
DX20	-	-	1	50	-	-
DX24	1	51	-	-	-	-



Pot life at 20°C: 4 hr



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.5	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.5	0.7 bar	atomisation pressure





2 coats

intermediate and final flash-off: 5 min



	DX24	DX20	DX18
20 °C	3 hr 30 min	5 hr	6 hr
60 - 65 °C	20 min	30 min	40 min



Guideline for short wave IR equipment

Half power: 5 min Full power: 15 - 20 min

VOC compliant

This product mix is not VOC compliant.

# DX49 2K HS EFFECTIVE CLEAR



### **Products**

DX49 2K HS Effective Clear

DX18 Activator Slow
DX20 Activator Standard

DX24 Activator Extra Fast

### **Product mix**





Mixing ratios with special agents are available in the productmix table on Colour Room and in the specific TDS.



DIN 4: 14 - 15 s at 20°C



55 - 65 µm (2 coats)



DX49 2K HS Effective Clear can be overcoated with itself within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

#### Remarks

- · Material has to be at room temperature (18-25°C) before use.
- · Allow additional time for preheating up to panel temperature.
- · Surplus ready for use material should not be returned to original can.
- If necessary for minor viscosity adjustments, use Duxone basecoat Thinner (maximum 5%).
- · Close can of clear and activator tightly immediately after use, as both products will react with humid air and water and lose their hardening effect.
- · Not to be used with Duxone Waterborne Basecoat.

# DX49 2K HS EFFECTIVE CLEAR



Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Duxone product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Duxone product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.